

INTRODUCTION

- The Medium Density Fibreboard (MDF) is an engineered wood product manufactured by breaking down hardwood or softwood residuals into wood fibres, and combining it with wax and a resin binder, which is forming panels by applying high temperature and pressure.
- The Melamine Faced Medium Density Fibreboard (MDF) is manufactured by high pressure and high heat bonding impregnated paper to Plain Medium Density Fibreboard, and provide a highly Scratch, Heat, Abrasion, Steam, and Chemical or Stain Resistant product surface finishing.

PRODUCT INFORMATION

PRODUCT	MEDIUM DENSITY FIBREBOARD	MEDIUM DENSITY FIBREBOARD
Grade	UF Non-Moisture Resistant	HMR V313 Moisture Resistant
Thickness	3mm, 6mm, 9mm, 12mm, 15mm, 16mm, 18mm & 25mm	9mm, 12mm, 15mm, 16mm, 18mm & 25mm
Size	4' x 8' (1220mm x 2440mm) *	
	4' x 9' (1220mm x 2745mm) *	
	6' x 8' (1830mm x 2440mm) *	
	6' x 9' (1830mm x 2745mm) *	
Colour / Design	Solid and Woodgrain Design **	
Surface Finishing	Texture / Woodgrain / Matt / Pearl / Stipple / Ashgrain / Finoline / Fabric / Timber Saw Cut / Saw Cut / SR	

* The board size only available on specified Colour and Design.

** Please refer to Melamine Collection for individual Colour and Woodgrain Design.

BOARD PROPERTY

PROPERTY	METHOD	UNIT	THICKNESS (mm)					
			3mm	6mm	9mm	12mm	15~18mm	25mm
Density	EN323	kg/m ³	830 ~ 800	800 ~ 760	780 ~ 740	760 ~ 720	730 ~ 690	700 ~ 660
Moisture Content	EN322	%	4 ~ 9	4 ~ 9	4 ~ 9	4 ~ 9	4 ~ 9	4 ~ 9
Modulus of Rupture	EN310	N/mm ²	35	35	32	30	28	25
Internal Bond	EN319	N/mm ²	0.75	0.75	0.7	0.7	0.65	0.6
Screw Holding - Face *	EN320	N	-	-	-	-	1050	1000
Screw Holding - Edge *	EN320	N	-	-	-	-	850	700
Thickness Swelling - UF **	EN317	%	35	30	17	15	12	10
Thickness Swelling - V313 HMR **	EN317	%	-	-	12	10	8	7
Thickness	EN324-1	mm	+/- 0.2 mm					
Length & Width	EN324-1	mm/m	+/- 2~5 mm/m					
Squareness	EN324-2	mm/m	2 mm/m					
Edge Straightness	EN324-2	mm/m	1.5 mm/m					
Latex Spots	-	spot	≤ 5 spots					
Size of Latex Spots	-	mm	≤ 6 mm					
Minor Stains / Fibre Marks / Scratch Lines	-	-	Free on 1 side					

* Screw holding only for thickness 15mm and above.

**24-hour immersion in 20 °C (+/- 1 °C) water.

CF ASIA TRADING SDN BHD (CO No 1006446-K) (GST No 000373145600)

No 41, Jalan Austin Perdana 5/22, Taman Austin Perdana, 81100 Johor Bahru, Johor, Malaysia.

Tel: 07-358 2818 Fax: 07-354 0818 E-mail: info@cfasiatrading.com Website: www.cfasiatrading.com

FORMALDEHYDE EMISSION

TYPE	METHOD	CLASSIFICATION
Class CARB Phase 2	ASTM D 6007	≤ 0.1 ppm
Class E1	EN120	≤ 8.0 mg / 100 g
Class E2	EN120	≤ 30.0 mg / 100 g
Class E3	EN120	> 30.0 mg / 100 g

MELAMINE SURFACE PROPERTY

TEXT	TEXT METHOD	REQUIREMENT
Scratch Resistant	Applying successively load to diamond scratching point of defined geometry and examine the marks produced.	Minimum load 2.5N.
Heat Resistant	1. Lighted cigarette placed on surface of test sample.	Stain easily removed by wet cloth.
	2. Sample placed in oven and baked at 70°C for 24 hours.	No Hairline cracks observed using a 6X magnifying glass.
	3. Aluminium container containing oil superheated to 180°C placed on sample for 20 minutes.	No marks or any changes observed.
Abrasion Resistant	Taber abraser applied at 500 gram on to sample surface.	Insignificant abrasion of surface sample.
Steam Resistant	Test sample placed on top of a beaker or boiling water for an hour.	No fault observed.
Chemical or Stain Resistant	Surface of test sample exposed to various chemicals and stains: Alkal Alcohol, Petroleum Product, Coffee, Animal Oil, Vegetable Oil / Sauce, Soup / Detergent, Tea, Vineger, Sugar, Ink, Lip-stick, Nail-Polish, Milk, Ammonium Chloride, Shoe-Polish.	No fault or stains observed on sample in all cases.

The above information and recommendation are meant guidelines solely offered for your consideration and verification.

Usage of the product may differ for each application and customers are strongly advised to carry out their own trials of suitability to meet their requirements.

We guarantee the product is produced to a uniform quality standard and under strict production control. However, since we do not have control over its use, we cannot be held responsible or liable for any damage resulting from wrongful usage of the product.

CF ASIA TRADING SDN BHD (CO No 1006446-K) (GST No 000373145600)

No 41, Jalan Austin Perdana 5/22, Taman Austin Perdana, 81100 Johor Bahru, Johor, Malaysia.

Tel: 07-358 2818 Fax: 07-354 0818 E-mail: info@cfasiatrading.com Website: www.cfasiatrading.com