

# Technical Data

## CONSEAL TOUCH-UP



### Product description

Conseal Touch-up is a quick drying high build acrylic primer/finish.

---

### Recommended use

Conseal Touch-up is a versatile and easy to use primer/finish for multipurpose use either direct to steel and other metals or for use as a touch up coat. It is a single component, high build coating which can be tinted to a large colour range.

---

### Film thickness and spreading rate

|  | Minimum | Maximum | Typical |
|--|---------|---------|---------|
| Film thickness, dry ( $\mu\text{m}$ )                | 75      | 120     | 120     |
| Film thickness, wet ( $\mu\text{m}$ )                | 150     | 245     | 245     |
| Theoretical spreading rate ( $\text{m}^2/\text{l}$ ) | 6,5     | 4,1     | 4,1     |

---

### Physical properties

Colour According to colour card and Multicolor tinting system (MCI)  
Solids (vol %)\*  $49 \pm 2$

Flash point  $25^\circ\text{C} \pm 2$  (Setaflash)

VOC 440 gms/ltr UK-PG6/23(97). Appendix 3

Gloss Semigloss

Gloss retention Good

Abrasion resistance Good

Solvent resistance Good

Chemical resistance Good

Flexibility Good

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### Bare steel

Cleanliness: Power tool cleaning to min. St 2, mill scale free (ISO 8501-1:1988). Improved surface treatment (blast cleaning to Sa 2½) will improve the performance.

#### Coated surfaces

Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information. For maintenance UHPWJ to WJ2 (NACE No.5/SSPC-SP 12) or Power tool cleaning to min. St 2 for rusted areas

Other surfaces

For aluminium and galvanized surface; degreasing, light abrading or sand sweeping.

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The temperature of the substrate should be minimum 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure correct drying.

---

## Application methods

Spray If airless spray is used the paint must be diluted 5-10 % with Jotun Thinner No. 7.  
Brush Use a suitable brush. Care must be taken to achieve the specified dry film thickness.  
Roller May be used, but is not recommended for first coat on bare metal. Care must be taken to achieve the specified dry film thickness.

---

## Application data

|                            |  |
|----------------------------|--|
| Mixing ratio (volume)      | Single pack.                                 |
| Thinner/Cleaner            | Jotun Thinner No. 7                          |
| Guiding data airless spray |  |
| Pressure at nozzle         | 15 MPa (150 kp/cm <sup>2</sup> , 2100 psi.). |
| Nozzle tip                 | 0.45-0.66 mm (0.018-0.026").                 |
| Spray angle                | 40 - 65°                                     |
| Filter                     | Check to ensure that filters are clean.      |

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

| Substrate temperature  | 5°C    | 10°C   | 23°C   | 40°C  |
|------------------------|--------|--------|--------|-------|
| Surface dry            | 40 min | 30 min | 20 min | 15 h  |
| Through dry            | 17 h   | 11 h   | 10 h   | 6 h   |
| Dry to recoat, minimum | 3 h    | 2,5 h  | 2 h    | 1,5 h |

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

1) Conseal Touch-up                      1 x 120 µm                      (Dry Film Thickness)  
or

2) Barrier 77                      1 x 40 µm                      (Dry Film Thickness)  
Conseal Touch-up                1 x 75 µm                      (Dry Film Thickness)

Other systems may be specified, depending on area of use

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

5 litre container  
or  
20 litre container

Packing may vary from country to country according to local requirements.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

---

## DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

Footer - English

| Head Office & Nordic  | Europe                     | Middle East             | South East Asia             |
|-----------------------|----------------------------|-------------------------|-----------------------------|
| Jotun A/S             | Jotun Paints (Europe) Ltd. | Jotun U.A.E Ltd. LLC.   | Jotun (Singapore) Pte. Ltd. |
| P.O. Box 2021         | Stather Road, Flixborough  |                         | No 11-15, Sixth Lok Yang    |
| N-3248 Sandefjord     | North Lincolnshire DN15    | Al Quoz Industrial Area | Road                        |
| Norway                | 8RR                        | P.O Box 3671            | Jurong                      |
| Phone +47 33 45 70 00 | United Kingdom             | Dubai U.A.E             | Singapore 628 111           |
| Fax +47 33 46 46 13   | Phone +44 172 44 00 000    | Phone +971 4 3 39 50 00 | Phone +65 6265 4711         |
|                       | Fax +44 172 44 00 100      | Fax +971 4 3 38 06 66   | Fax +65 6265 7484           |

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 25 AUGUST 2005 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

