

Technical Data

HARDTOP AS



Product description

Hardtop AS is a two-pack polyurethane topcoat with excellent gloss and colour retention.

Recommended use

As topcoat over an epoxy/epoxymastic system where a durable, high gloss finish is required in aggressive atmospheric exposure. Cures at low temperatures.

Film thickness and spreading rate

| | Minimum | Maximum | Typical |
|--|---------|---------|---------|
| Film thickness, dry (μm) | 40 | 60 | 50 |
| Film thickness, wet (μm) | 80 | 120 | 100 |
| Theoretical spreading rate (m^2/l) | 12,5 | 8,3 | 10 |

Physical properties

Colour According to colour card and Multicolor tinting system (MCI)
Solids (vol %)* 50 ± 2

Flash point $26^\circ\text{C} \pm 2$ (Setaflash)

VOC 415 gms/ltr UK-PG6/23(97). Appendix 3

Gloss Glossy
Gloss retention Excellent
Water resistance Very good
Abrasion resistance Very good
Solvent resistance Very good
Chemical resistance Very good
Flexibility Very good

*Measured according to ISO 3233:1998 (E)

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Coated surfaces

Clean, dry and undamaged compatible primer. Please contact your local Jotun office for more information.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 0°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Application methods

Spray Use airless spray
Brush Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

Application data

Mixing ratio (volume) 4 parts of Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent).

Pot life (23°C) 4 hours (Reduced at higher temp.).

Thinner/Cleaner Jotun Thinner No. 10

Guiding data airless spray

| | |
|--------------------|---|
| Pressure at nozzle | 15 MPa (150 kp/cm ² , 2100 psi). |
| Nozzle tip | 0.33-0.46 mm (0.013-0.018"). |
| Spray angle | 40-80° |
| Filter | Check to ensure that filters are clean. |

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

| Substrate temperature | 0°C | 5°C | 10°C | 23°C | 40°C |
|-------------------------------------|------|------|------|------|-------|
| Surface dry | 8 h | 4 h | 2 h | 1 h | 0,5 h |
| Through dry | 40 h | 30 h | 16 h | 8 h | 4 h |
| Cured | 20 d | 15 d | 10 d | 5 d | 2 d |
| Dry to recoat, minimum | 24 h | 18 h | 10 h | 5 h | 2,5 h |
| Dry to recoat, maximum ¹ | | | | | |

1. The surface must be free from any chalking or any other contamination and if necessary, sufficiently roughened prior to application.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

| | | |
|---------------|------------|----------------------|
| Jotamastic 87 | 2 x 150 µm | (Dry Film Thickness) |
| Hardtop AS | 1 x 50 µm | (Dry Film Thickness) |

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

20 litre unit: 16 litres Comp. A in a 20 litre container and 4 litres Comp. B in a 5 litre container.
or
5 litre unit: 4 litres Comp. A in a 5 litre container and 1 litre Comp. B in a 1 litre container.
Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Footer - English

| Head Office & Nordic | Europe | Middle East | South East Asia |
|-----------------------|----------------------------|-------------------------|-----------------------------|
| Jotun A/S | Jotun Paints (Europe) Ltd. | Jotun U.A.E Ltd. LLC. | Jotun (Singapore) Pte. Ltd. |
| P.O. Box 2021 | Stather Road, Flixborough | | No 11-15, Sixth Lok Yang |
| N-3248 Sandefjord | North Lincolnshire DN15 | Al Quoz Industrial Area | Road |
| Norway | 8RR | P.O Box 3671 | Jurong |
| Phone +47 33 45 70 00 | United Kingdom | Dubai U.A.E | Singapore 628 111 |
| Fax +47 33 46 46 13 | Phone +44 172 44 00 000 | Phone +971 4 3 39 50 00 | Phone +65 6265 4711 |
| | Fax +44 172 44 00 100 | Fax +971 4 3 38 06 66 | Fax +65 6265 7484 |

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 31 AUGUST 2005 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED