# Technical Data GALVANITE



### Product description

Galvanite is a single pack, zinc-rich primer for repair of damaged or degraded galvanized surfaces or as a zinc primer for properly prepared steel surfaces

#### Recommended use

General purpose primer for repair of welding or other damage to galvanized surfaces. May also be used as a zinc-rich primer for steel surfaces.

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (µm)	30	75	40
Film thickness, wet (µm)	55	135	70
Theoretical spreading rate (m <sup>2</sup> /l)	7,3	18,3	13,8

### Physical properties

Colour Light metallic grey. Weathers to a galvanized appearance

Solids (vol %)\*  $55 \pm 2$ 

Flash point  $25^{\circ}\text{C} \pm 2 \text{ (Setaflash)}$ 

Abrasion resistance Good Chemical resistance Good Flexibility Good

\*Measured according to ISO 3233:1998 (E)

### Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

#### Condition during application

The temperature of the substrate should be minimum 5°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.

#### Application methods

Spray Conventional or airless spray may be used for larger areas.

Brush Recommended Roller Recommended

GALVANITE Page 1 of 3

## Application data

Thinner/Cleaner
Guiding data airless spray

Guiding data airless spray Pressure at nozzle

Nozzle tip Spray angle

Filter

Jotun Thinner No. 7

5-10MPa(700-1400 psi) 0.38-0.53 mm(0.015-.021")

40-80°

Check to ensure that filters are clean

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

Substrate temperature	5°C	10°C	23°C	40°C
Surface dry	2 h	1 h	30 min	7 min
Through dry	8 h	4 h	2 h	45 min
Dry to recoat, minimum	48 h	24 h	16 h	6 h

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

### Typical paint system

Galvanite 2x40 micron (Dry Film Thickness)

Other systems may be specified, depending on area of use

### Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

### Handling

Handle with care. Stir well before use.

### Packing size

4 litre and 1 litre

Packing may vary from country to country according to local requirements.

GALVANITE Page 2 of 3

### Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

#### DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Head Office & Nordic Europe Middle Fast South Fast Asia Jotun U.A.E Ltd. LLC. Jotun A/S Jotun Paints (Europe) Ltd. Jotun (Singapore) Pte. Ltd. No 11-15, Sixth Lok Yang P.O. Box 2021 Stather Road, Flixborough Al Quoz Industrial Area North Lincolnshire DN15 Road N-3248 Sandefjord 8RR P.O Box 3671 Jurona Norway Dubai U.A.E United Kingdom Singapore 628 111 Phone +47 33 45 70 00 Phone +44 172 44 00 000 Phone +65 6265 4711 Fax +47 33 46 46 13 Phone +971 4 3 39 50 00 Fax +65 6265 7484 Fax +44 172 44 00 100 Fax +971 4 3 38 06 66

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 19 SEPTEMBER 2005 BY JOTUN THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

GALVANITE Page 3 of 3