

Technical Data

JOTAMASTIC 87 ALUMINIUM



Product description

Jotamastic 87 Aluminium is a two-pack surface tolerant, abrasion resistant, high solids epoxy mastic coating which may be applied in high film thickness. Available with different hardeners for varying substrate temperatures, Standard (Std) and Cold Climate (CC)/Wintergrade (WG). This product is a part of a complete system which is certified not to spread flames.

Recommended use

Steel where blast cleaning may not be possible, and on hydrojetted surfaces still being moist where gloss retention is of minor importance. Can be used alone or in combination with various systems of primers and topcoats. Gives excellent corrosion protection both in salt and fresh water. If exposed to sunlight chalking may occur.

Film thickness and spreading rate

Std Comp. B	Minimum	Maximum	Typical
Film thickness, dry (μm)	150	300	200
Film thickness, wet (μm)	170	345	230
Theoretical spreading rate (m^2/l)	5,8	2,9	4,4

CC/WG Comp. B	Minimum	Maximum	Typical
Film thickness, dry (μm)	150	250	200
Film thickness, wet (μm)	195	325	260
Theoretical spreading rate (m^2/l)	5,1	3,1	3,9

Approvals

APAS approved to specification 2973, 2973F and 2977.

(These approvals are just a few examples of available approvals. Please contact Jotun for details)

Physical properties

Colour	Aluminium, Aluminium Red toned
Solids (vol %)*	87 ± 2 Std Comp. B 77 ± 2 CC/WG Comp. B
Flash point	Std Comp. B: 40°C ± 2 (Setaflash) CC/WG Comp. B: 31°C ± 2 (Setaflash)
VOC	Std Comp. B 2,09 lbs/gal (250 gms/ltr) USA-EPA Method 24 110 gms/ltr UK-PG6/23(97). Appendix 3 CC/WG Comp. B 180 gms/ltr UK-PG6/23(97). Appendix 3
Gloss	Semi-gloss
Gloss retention	Fair
Water resistance	Excellent
Abrasion resistance	Very good
Solvent resistance	Good
Chemical resistance	Good
Flexibility	Good

*Measured according to ISO 3233:1998 (E)

Surface preparation

All surfaces should be clean and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Bare steel

Cleanliness: Power tool cleaning to min. St 2, mill scale free (ISO 8501-1:1988). Improved surface treatment (blast cleaning to Sa 2½) will improve the performance. In case of hydrojetting the flash rust degree shall not exceed moderate in SSPC and NACE standards for water prepared surfaces.

Shopprimed steel

Clean, dry and undamaged approved shopprimer.

Coated surfaces

Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information. For maintenance UHPWJ to WJ2 (NACE No.5/SSPC-SP 12) or Power tool cleaning to min. St 2 for rusted areas

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum +10°C (Std) (-5°C in CC/WG) and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure proper drying.

Hydrojetting of steel surface makes a wet surface. The surrounding air must have a relative humidity not exceeding 85 %. Before painting the surface shall not be glossy with moisture, but can have a patchy appearance.

Application methods

Spray	Use airless spray (thin 10%)
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller	May be used for small areas but not recommended for first primer coat, however when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Application data

Mixing ratio (volume)	Std Comp. B: 5.5 parts Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent) CC/WG Comp. B: 3.7 parts Comp. A (base) to be mixed thoroughly with 1 part comp. B (curing agent)
Induction time	10 minutes.
Pot life (23°C)	Std Comp. B: 1½ hours CC/WG Comp. B: 1 hour
Thinner/Cleaner	Jotun Thinner No. 17
Guiding data airless spray	
Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi).
Nozzle tip	0.53 - 0.79 mm (0.021-0.031")
Spray angle	65-80°
Filter	Check to ensure that filters are clean.

Note	* The temperature of the mixture of base and curing agent is recommended to be at least 15°C, otherwise extra solvent may be required to obtain correct viscosity. * Too much solvent results in lower sag resistance and slower cure. * If extra solvent is necessary, this should be added after mixing of the two components.
------	--

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Std Comp. B					
Substrate temperature		10°C	23°C	40°C	
Surface dry		8 h	4 h	2 h	
Through dry		24 h	10 h	4 h	
Cured		14 d	7 d	2 d	
Dry to recoat, minimum		24 h	10 h	4 h	
Dry to recoat, maximum ¹					
CC/WG Comp. B					
Substrate temperature	-5°C	0°C	5°C	10°C	23°C
Surface dry	24 h	18 h	12 h	6 h	2,5 h
Through dry	48 h	26 h	18 h	12 h	5 h
Cured		14 d	7 d	3 d	2 d
Dry to recoat, minimum	48 h	26 h	18 h	12 h	5 h
Dry to recoat, maximum ¹					

1. Provided the surface is free from chalking and other contamination prior to application, there is normally no overcoating time limit. Best intercoat adhesion occurs, however, when the subsequent coat is applied before preceding coat has cured. If the coating has been exposed to direct sunlight for some time, special attention must be paid to surface cleaning and mattening/removal of the surface layer in order to obtain good adhesion.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotamastic 87 Aluminium	1 x 200 µm	(Dry Film Thickness)
Jotamastic 87	1 x 200 µm	(Dry Film Thickness)
Hardtop AS	1 x 50 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

14,7 litres Comp. A (base) in a 20 litre container and 2.7 litres Std Comp. B (curing agent) in a 3 litre container
and
14,7 litres Comp. A (base) in a 20 litre container and 4 litres CC/WG Comp. B (curing agent) in a 5 litre container

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Footer - English

Head Office & Nordic	Europe	Middle East	South East Asia
Jotun A/S	Jotun Paints (Europe) Ltd.	Jotun U.A.E Ltd. LLC.	Jotun (Singapore) Pte. Ltd.
P.O. Box 2021	Stather Road, Flixborough		No 11-15, Sixth Lok Yang
N-3248 Sandefjord	North Lincolnshire DN15	Al Quoz Industrial Area	Road
Norway	8RR	P.O Box 3671	Jurong
Phone +47 33 45 70 00	United Kingdom	Dubai U.A.E	Singapore 628 111
Fax +47 33 46 46 13	Phone +44 172 44 00 000	Phone +971 4 3 39 50 00	Phone +65 6265 4711
	Fax +44 172 44 00 100	Fax +971 4 3 38 06 66	Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 25 AUGUST 2005 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED