# Technical Data JOTAPROOF TOPCOAT



### Product description

Jotaproof Topcoat is a two-pack acrylic topcoat with excellent gloss and colour retention.

#### Recommended use

As topcoat over an epoxy/epoxymastic system where a durable, high gloss finish is required in aggressive atmospheric exposure. Cures at low temperatures.

## Film thickness and spreading rate

•	Ŭ	Minimum	Maximum	Typical
Film thickness, dry (µm)		60	125	75
Film thickness, wet (µm)		95	200	120
Theoretical spreading rate (m <sup>2</sup> /l)		10,5	5	8,4

### Physical properties

Colour Solids (vol %)*	According to colour card and Multicolor tinting system (MCI) $63 \pm 2$

Flash point $31^{\circ}C \pm 2$  (Setaflash)

VOC 310 gms/ltr UK-PG6/23(97). Appendix 3

Gloss	Glossy
Gloss retention	Excellent
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Very good
Chemical resistance	Very good
Flexibility	Very good
*Measured according	to ISO 3233:1998 (E)

### Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Coated surfaces Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

### Condition during application

The temperature of the substrate should be minimum 5°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.

### Application methods

Spray	Use airless spray
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

### Application data

Mixing ratio (volume)	4 parts of Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent).
Pot life (23°C)	3 hours (Reduced at higher temp.).
Thinner/Cleaner Guiding data airless spray Pressure at nozzle Nozzle tip Spray angle Filter	Jotun Thinner No. 26 15 MPa (150 kp/cm <sup>2</sup> , 2100 psi). 0.33-0.46 mm (0.013-0.018"). 40-80° Check to ensure that filters are clean.

#### Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

Substrate temperature	5°C	10°C	23°C	40°C
Surface dry	6 h	5 h	3,5 h	2 h
Through dry	8 h	7 h	4 h	2 h
Cured	15 d	10 d	5 d	3 d
Dry to recoat, minimum	8 h	7 h	4 h	3 h
Dry to recoat, maximum <sup>1</sup>				

1. The surface must be free from any chalking or any other contamination and if necessary, sufficiently roughened prior to application.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

### Typical paint system

Barrier Jotamastic Plus 1 x 50 μm 1 x 250 μm (Dry Film Thickness) (Dry Film Thickness) Other systems may be specified, depending on area of use

#### Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed. Shelf Life Comp. A: 2 years Shelf LIfe Comp. B: 1 year

#### Handling

Handle with care. Stir well before use.

#### Packing size

20 litre unit: 16 litres Comp. A (base) in a 20 litre container and 4 litres Comp. B (curing agent) in a 5 litre container or

5 litre unit: 4 litres Comp. A (base) in a 5 litre container and 1 litre Comp. B. (curing agent) in a 1 litre container

Packing may vary from country to country according to local requirements.

#### Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

#### DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice. Footer - English

Head Office & Nordic Jotun A/S	Europe Jotun Paints (Europe) Ltd.	Middle East Jotun U.A.E Ltd. LLC.	South East Asia Jotun (Singapore) Pte. Ltd.	
P.O. Box 2021	Stather Road, Flixborough		No 11-15, Sixth Lok Yang	
N-3248 Sandefjord	North Lincolnshire DN15	Al Quoz Industrial Area	Road	
Norway	8RR	P.O Box 3671	Jurong Singapore 628 111	
Phone +47 33 45 70 00	7 33 45 70 00 United Kingdom	Dubai U.A.E		
Fax +47 33 46 46 13	Phone +44 172 44 00 000		Phone +65 6265 4711	
	Fax +44 172 44 00 100	Phone +971 4 3 39 50 00 Fax +971 4 3 38 06 66	Fax +65 6265 7484	

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 29 NOVEMBER 2005 BY JOTUN THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

#### JOTAPROOF TOPCOAT