

# Technical Data

## PENGUARD CLASSIC MIO



### Product description

Penguard Classic MIO is a high build, two-pack epoxy coating pigmented with micaceous iron oxide and based on epoxy resin with high molecular weight. Two hardeners (Comp. B) are available for varying substrate temperatures, Standard (Std) and Cold Climate (CC).

---

### Recommended use

As an anti-corrosive primer and/or intermediate coating for protection of steel and other substrates. Can be used alone or in various systems of primers and topcoats.

---

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry ( $\mu\text{m}$ )	100	160	100
Film thickness, wet ( $\mu\text{m}$ )	160	260	160
Theoretical spreading rate ( $\text{m}^2/\text{l}$ )	6,2	3,9	6,2

---

### Physical properties

Colour	Grey, Red
Solids (vol %)*	62 $\pm$ 2
Flash point	25°C $\pm$ 2 (Setaflash)
Gloss	Flat
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Excellent
Chemical resistance	Excellent
Flexibility	Good

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### Bare steel

Cleanliness: Blast cleaning to Sa 2½ (ISO 8501-1:1988). Roughness: using abrasives suitable to achieve grade Fine to Medium G (30-85  $\mu\text{m}$ , Ry5) (ISO 8503-2)

#### Shopprimed steel

Clean, dry and undamaged approved shopprimer.

#### Coated surfaces

Clean, dry and undamaged compatible primer. Please contact your local Jotun office for more information.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The temperature of the substrate should be minimum +10°C (Std) (0°C in CC) and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure proper drying. The coating should not be exposed to oil, chemicals or mechanical stress until cured.

---

## Application methods

Spray Use airless spray  
Brush Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

---

## Application data

Mixing ratio (volume)	4 parts Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent)
Mixing	30 minutes prior to use
Pot life (23°C)	Penquard Classic Std. Comp. B: 6 hours (Reduced at higher temperature) Penquard Classic CC Comp. B: 2 hours (Reduced at higher temperature)
Thinner/Cleaner	Jotun Thinner No. 17
Guiding data airless spray	
Pressure at nozzle	15 MPa (150 kp/cm <sup>2</sup> , 2100 psi)
Nozzle tip	0.46-0.69(0.018-0.027")
Spray angle	40-80
Filter	Check to ensure that filters are clean

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

Std. Comp. B				
Substrate temperature		10°C	23°C	40°C
Surface dry		2 h	1 h	0,5 h
Through dry		14 h	7 h	3,5 h
Cured		14 d	7 d	3 d
Dry to recoat, minimum		14 h	7 h	3,5 h
Dry to recoat, maximum <sup>1</sup>				
CC Comp. B				
Substrate temperature	0°C	5°C	10°C	23°C
Surface dry	10 h	5 h	2 h	1 h
Through dry	24 h	16 h	8 h	4 h
Cured	-	16 d	8 d	4 d
Dry to recoat, minimum	24 h	16 h	8 h	4 h
Dry to recoat, maximum <sup>1</sup>				

1 Provided the surface is free from chalking and other contamination prior to application, there is normally no overcoating time limit. Best intercoat adhesion occurs, however, when the subsequent coat is applied before preceding coat has cured. If the coating has been exposed to direct sunlight for some time, special attention must be paid to surface cleaning and mattening/removal of the surface layer in order to obtain good adhesion.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

Penguard Classic MIO	1 x 100 microns	(Dry Film Thickness)
Penguard Classic	1 x 100 microns	(Dry Film Thickness)
Hardtop AS	1 x 50 microns	(Dry Film Thickness)

Other systems may be specified, depending on area of use

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

16 litres Comp. A (base) in a 20 litre container and 4 litres Comp. B (curing agent) in a 5 litre container

4 litres Comp. A (base) in a 5 litre container and 1 litre Comp. B (curing agent) in a 1 litre container

Packing may vary from country to country according to local requirements.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

---

### DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

Footer - English

Head Office & Nordic	Europe	Middle East	South East Asia
Jotun A/S	Jotun Paints (Europe) Ltd.	Jotun U.A.E Ltd. LLC.	Jotun (Singapore) Pte. Ltd.
P.O. Box 2021	Stather Road, Flixborough		No 11-15, Sixth Lok Yang
N-3248 Sandefjord	North Lincolnshire DN15	Al Quoz Industrial Area	Road
Norway	8RR	P.O Box 3671	Jurong
Phone +47 33 45 70 00	United Kingdom	Dubai U.A.E	Singapore 628 111
Fax +47 33 46 46 13	Phone +44 172 44 00 000	Phone +971 4 3 39 50 00	Phone +65 6265 4711
	Fax +44 172 44 00 100	Fax +971 4 3 38 06 66	Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 19 SEPTEMBER 2005 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED