

Technical Data

Jotafloor Rapid Dry WB



Product description

Jotafloor Rapid Dry WB is a single component, fast drying, semigloss emulsion based topcoat, offering durability with good UV protection and aesthetics.

Recommended use

Ideal for floors requiring a fast, easy to use, light duty floor coating where drying time is at premium:

- Exhibition halls
- In-house events
- Concerts/Sports venues/Open Days etc.

Also as a general purpose floor coating offering protection from mild spillages and light pedestrian traffic.

- Factory
 - Warehouse
 - Domestic Applications
 - Garage show rooms
-

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	25	50	35
Film thickness, wet (μm)	70	140	100
Theoretical spreading rate (m^2/l)	14,4	7,2	10,3

Physical properties

Colour	White and colours available in Jotun Multicolor tinting system.
Solids (vol %)*	36 ± 2

Flash point

VOC	1,3 lbs/gal (155 gms/ltr) USA-EPA Method 24
------------	---

Gloss	Semigloss
--------------	-----------

Gloss retention	Good
------------------------	------

Water resistance	Fair
-------------------------	------

Abrasion resistance	Good
----------------------------	------

Flexibility	Good
--------------------	------

*Measured according to ISO 3233:1998 (E)

Surface preparation

All concrete damaged by exposure to chemicals, contaminated by any substance or unsound in any way, shall be removed to expose sound concrete.

Coated surfaces

Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information.

Other surfaces

The surface must be sound, clean and dry. Surface contamination to be removed by detergent and fresh water cleaning.

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure correct drying.

Application methods

Spray Use airless spray (thin 5%)

Brush Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

Roller May be used. However when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Application data

Mixing ratio (volume) Single pack.

Thinner/Cleaner Water

Guiding data airless spray

Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi)
Nozzle tip	0.43-0.48 mm (0.017-0.019")
Spray angle	40-80°
Filter	Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	10°C	23°C	40°C
Surface dry	60 min	45 min	25 min
Through dry	4 h	2 h	1 h
Dry to recoat, minimum ¹	4 h	2 h	1 h

1. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotafloor Sealer WB	1 Coat	
Jotafloor Rapid Dry WB	2-3 x 35 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

5 litres

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used under conditions beyond our control, we can only guarantee the quality of the product itself. We also reserve the right to change the given data without notice. Minor product variations may be implemented in order to comply with local requirements.

If there is any inconsistency in the text the English (UK) version will prevail.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 3 JULY 2013 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED