
Product Data

SK 34 Firebrick

Chemical Analysis

Al ₂ O ₃	38 %
SiO ₂	59 %
Fe ₂ O ₃	2.5 %

Refractoriness 1400°C

Bulk Density 2.05g/cm²

Apparent Porosity 25%

Cold Crushing Strength 300 kg/cm²

Refractoriness Under Load at 2 kgf/cm² 1300°C

Permanent Linear Change At Temperature (+0.1/-0.4) at 1300°C

Service Temperature 1300°C

Origin China