



**PROGENLLITE**

## PROGENLLITE COBALT GRADE 6 TIG CAST ROD

TIG hardfacing alloy solutions for wear, heat and corrosion resistant application


### CLASSIFICATION

AWS 5.21 / ERCoCr-A

### WELD DEPOSIT HARDNESS

Single Layer :38-40 HRC

### NOMINAL WELD DEPOSIT CHEMISTRY



Co	Cr	W	C	Ni	Mo	Fe	Si	Others
Bal	29	4.5	1.0	3.0	0.5	3.0	1.0	Bal.

### TYPICAL APPLICATION

Suitable for hardfacing valve seat inserts, bearing, cutter edges, rotary rings, saw tips, cutting tools, shredding tools, extrusion dies, mixing tools or extrusion screws in the wood, paper and plastics industries.

### CHARACTERISTICS

Cobalt-based alloy with a combination of chemical elements to resist high temperatures and give longer wear life.

### AVAILABLE SIZES

TIG CAST ROD  
Dia / mm

3.2mm x 350mm

**Lincoln Energy Sdn Bhd** (908445-A)

No.13 and 15, Jalan BP 5, Bandar Bukit Puchong 47100 Puchong, Selangor Darul Ehsan.  
Tel: +603-8060 6131 Fax:+603-8060 6639 Email: sales@lincoln-energy.com