KFOIL K710N

SINGLE SIDED REFLECTIVE ALUMINIUM PAPER FOIL

- Single Sided Aluminium Foil (99% Pure Aluminium) with high reflectivity (>0.98) and low emissivity (<0.02) surface
- Special bonding layer giving superior vapour barrier
- Coupling with minimum of 10mm air space can cut down heat transfer by conduction & convection to negligible figure

SARKING MEMBRANE | VAPOR BARRIER | HEAT INSULATION | ENERGY EFFICIENCY
COST EFFECTIVE | LOW MAINTENANCE FEE | DURABLE | ECO FRIENDLY
LIGHT IN WEIGHT | EASY INSTALLATION | TRANSPORTABILITY

K710N LAYOUT



PAPER BASED	-
GRAMMAGE	85 – 95 gsm
THICKNESS	110 – 160 micron
TENSILE STRENGTH (ASTM D 828)	MD: 3 – 4 kN/m XD: 3 – 4 kN/m
CORROSION/DELAMINATION (95% RH @50°C,30 DAYS	None
TEAR RESISTANCE	Good
VAPOUR BARRIER	Good
WATER RESISTANCE	No Delamination

Technical information provided in this data sheet are typical laboratory averages and are used subject to variation. While the information is believed to be reliable and correct. No guarantee or warranty (expressed or implied) can be made regarding specific applications or patent rights. Product specifications are subject to change without prior notice.



RECOMMENDED APPLICATION

- Metal roofing insulation
- Concrete / Clay title roofing insulation
- Building wrapping
- Wall insulation
- Floor insulation
- Foil facing for bulk installation
- Industrial packaging
- Thermal tank
- Etc



	UV light	Moisture
	transmittance	penetration
Aluminium Foil, 7µ	0 %	0 g/m².day
Metalized PET, 12μ	5 %	0.8 g/m².day
PE Transparent, 20μ	95 %	3.7 g/m ² .day
PE Opaque, 20μ	30 %	3.7 g/m ² .day
PET Film, 13μ	91 %	31 g/m ² .day
PVC Film, 250μ	-	3.0 g/m².day
ΡΡ, 300μ	-	0.2 g/m ² .day

(Data sourced from internet)

SIZE AVAILABILITY

Width(m)	Length(m)	Optimum pallet packing
1.22 ± 1%	45 ± 2%	150 Rolls
1.22 ± 1%	60 ± 2%	130 Rolls

Customise size are available upon request within machine limits.



K FOIL INSULATION (MALAYSIA) SDN BHD

950435-D

9 & 11, KILANG BERKEMBAR, LORONG IKS BUKIT MINYAK 1D, 14000 S.P.T, PENANG, M'SIA

