

Material Group	Group No	Material Examples*	Brinell hardness	d.o.c [mm]		feed [mm/rev]		A max [mm ²]	V _c [m/min]		Optimal cutting conditions	
				min	max	min	max		min	max	d.o.c	feed
Low Carbon Steel	1	Ck15, Ck45 1020, 1045	150	0.50	2.0	0.15	0.35	0.64	180	350	1.0	0.35
			180		2.0		0.35	0.64		280		
			210		1.5		0.35	0.56		250		
Alloy Steel	2	42 CrMo 4 St 50-2 Ck60 1060 4140	180	0.50	2.0	0.15	0.30	0.56	120	280	1.0	0.30
			230		2.0		0.30	0.48		250		
			280		2.0	0.13	0.30	0.40		210		
			320		1.5	0.25	0.32	180				
High Alloy Steel	3	X40 CrMoV 5 1 H 13 40 NiCrMo 6 4340 S 2-10-1-8 HSS M42	220	0.50	2.0	0.13	0.30	0.48	70	190	1.0	0.28
			280		2.0		0.30	0.40		150		
			320		1.5		0.30	0.32		130		
			350		1.5		0.25	0.24		100		
			400	0.50	1.2	0.22	0.17	50	90	0.9	0.20	
			480		1.0	0.08	0.18	0.12	40	80	0.7	0.16
			550		0.8	0.14	0.10	30	70	0.6	0.12	
Austenitic Stainless Steel	4	X5 CrNi 18 9 304	210 to 250	0.50	2.0	0.14	0.25	0.32	170	270	1.0	0.35
			230 to 270		2.0	0.13	0.18	0.24	120	210	1.0	0.32
			-----		1.5	0.13	0.18	0.24	70	120	1.0	0.28
Ferritic Stainless Steel	7	X8 Cr 7 430	Annealed	0.50	2.0	0.15	0.20	0.32	170	250	1.0	0.32
Martensitic Stainless Steel	8	X15 Cr 13 410	Annealed Treated	0.50	2.0	0.15	0.20	0.32	170 120	250 210	1.0	0.32
Grey Cast Iron	9	GG 20 GG 25 GG 30	140 to 230	0.50	2.0	0.11	0.45	0.80	170	280	1.0	0.35
			0.72					250				
			0.72					230				
Nodular Cast Iron	10	GGG 40 GGG 50 GGG 70 G-X260NiCr42	210	0.50	2.0	0.11	0.35	0.60	120	230	1.0	0.30
			260					0.52		190		
			310					0.48		150		
			450	0.20	1.0	0.04	0.10	0.08	30	50	0.6	0.07
Nickel Based Alloys	11	Inconel 625 Inconel 718 Hastelloy C	-----	0.50	1.5	0.13	0.18	0.20	25	35	1.0	0.28
			0.20					28		40		
			0.24					40		65		
Titanium Based Alloys	12	TiAl 6 V4 T40	-----	0.50	1.5	0.13	0.18	35	60	1.0	0.30	
			0.15				0.24		28			40

RCMT

Insert designation Super Finishing Finishing Semi Finishing Roughing Interrupted Cut

RCMT 0602 M0

