

Material Group	Group No	Material Examples*	Brinell hardness	d.o.c [mm]		feed [mm/rev]		A max [mm <sup>2</sup> ]	V <sub>c</sub> [m/min]		Optimal cutting conditions				
				min	max	min	max		min	max	d.o.c	feed			
Low Carbon Steel	1	Ck15, Ck45 1020, 1045	150	0.50	5.0	0.27	0.68	3.1	180	330	4.0	0.50			
			180		5.0		0.68			3.1			280		
			210		5.0		0.60			2.6			250		
Alloy Steel	2	42 CrMo 4 St 50-2 Ck60 1060 4140	180	0.50	5.0	0.27	0.60	2.6	120	280	4.0	0.45			
			230		5.0		0.60			2.0			250		
			280		5.0	0.23	0.53	2.0		210					
			320		4.0	0.23	0.53	1.7		180					
High Alloy Steel	3	X40 CrMoV 5 1 H 13 40 NiCrMo 6 4340 S 2-10-1-8 HSS M42	220	0.50	5.0	0.23	0.60	2.0	70	190	4.0	0.40			
			280		5.0		0.60			2.0			150		
			320		4.0		0.53			1.6			130		
			350		4.0		0.53			1.6			100		
			400	3.5	0.14	0.45	1.2	50		90			3.4	0.36	
			480	0.50	3.0	0.14	0.35	0.9		40			80	2.9	0.30
			550	2.5	0.28	0.6	30	70		2.5			0.25		
Austenitic Stainless Steel	4	X5 CrNi 18 9 304	210 to 250	0.50	5.0	0.26	0.52	1.7	170	270	4.0	0.40			
	5	X2 CrNiMo 17 2 2 316	230 to 270		5.0	0.23	0.46	1.4	160	210	4.0	0.36			
	6	X6 CrNiMoTi 17 12 2 316 Ti Duplex / Nitronic	-----		5.0	0.23	0.46	1.0	70	150	4.0	0.32			
Ferritic Stainless Steel	7	X8 Cr 7 430	Annealed	0.50	5.0	0.29	0.46	1.5	170	250	4.0	0.35			
Martensitic Stainless Steel	8	X15 Cr 13 410	Annealed Treated	0.50	5.0	0.29	0.46	1.5	170 120	250 190	4.0	0.35			
Grey Cast Iron	9	GG 20	140 to 230	0.50	5.0	0.20	0.90	3.0	170	250	4.0	0.60			
		GG 25						2.7		230					
		GG 30						2.7		210					
Nodular Cast Iron	10	GGG 40	210	0.50	5.0	0.20	0.70	2.3	120	230	4.0	0.50			
		GGG 50	260					2.0		190					
		GGG 70	310					1.8		150					
		G-X260NiCr42	450					0.50		1.8			0.06	0.15	0.3
Nickel Based Alloys	11	Inconel 625	-----	0.50	5.0	0.26	0.46	1.4	25	35	3.0	0.38			
		Inconel 718	-----					1.4	28	40					
		Hastelloy C	-----					1.6	40	65					
Titanium Based Alloys	12	TiAl 6 V4	-----	0.50	5.0	0.23	0.46	35	60	3.0	0.38				
		T40	-----				0.39	1.2	28	40	3.0	0.32			

Insert designation Super Finishing Finishing Semi Finishing Roughing Interrupted Cut

WNMG 080412 NN



LAMINA TECHNOLOGIES