



# SELECTARC BRAZING

## BRAZARGENT 5034 BARE RODS

Cadmium Free Silver (34%) Brazing Alloy

Diameter	Standard Package	Standard Length	List Price	Discount
1.5mm	1kg	500mm		
2.0mm	1kg	500mm		
2.5mm	1kg	500mm		

## BRAZARGENT 5045 BARE RODS / COATED RODS

Cadmium Free Silver (45%) Brazing Alloy

Diameter	Standard Package	Standard Length	List Price	Discount
1.5mm	1kg	500mm		
2.0mm	1kg	500mm		
2.5mm	1kg	500mm		

### Characteristics

BRAZARGENT 5045 is a widely used Cd free alloy which main elements are: Copper, Zinc, high Silver (45%) and Tin contents. Silver and Tin contents lowers the melting point, increases fluidity and exhibits good wetting properties.



PRODUCTS COMPLIANT WITH THE RESTRICTION OF HAZARDOUS SUBSTANCES DIRECTIVE (RoHS)



### Characteristics

BRAZARGENT 5034 is a very widely used Cd free alloy which main elements are: Copper, Zinc, Silver (34%) and Tin. Silver and Tin contents lowers the melting point, increases fluidity and exhibits good wetting properties.

## BRAZARGENT 5056 BARE RODS / COATED RODS / TBW

Cadmium Free Silver (56%) Brazing Alloy

Diameter	Standard Package	Standard Length	List Price	Discount
1.5mm	1kg	500mm		
2.0mm	1kg	500mm		
2.5mm	1kg	500mm		

### Characteristics

BRAZARGENT 5056 is a widely used Cd free alloy which main elements are: Copper, Zinc, high Silver (56%) and Tin contents (5%). Silver and Tin contents lowers the melting point, increases fluidity and exhibits good wetting properties. Its excellent fluidity makes it suitable in closely fitting joints as able to penetrate very tight gaps.



FORGING & FOUNDRY



FOOD INDUSTRY



NUCLEAR AND THERMAL PLANTS, POWER INDUSTRY



MINING INDUSTRY



SHIPBUILDING INDUSTRY



AUTOMOBILE INDUSTRY



CHEMICAL AND PETROCHEMICAL INDUSTRY



M&R INDUSTRY