N-048

NEOPRENE SEALANT

DESCRIPTION:

X' **CPASCAI**[®] N-048 NEOPRENE IS A ONE PART SEALER MAINLY CONSISTS NEOPRENE RUBBER AND SYSTHETIC RESIN. IT IS A SPECIAL FORMULATED SEALANT THAT CURES TO A TOUGH, FLEXIBLE BOND TO ALL ENGINEERING MATERIAL SURFACES. BECAUSE OF ITS EXCELLENT ELASTICITY AND WATER RESISTIVITY, IT IS MOST SUITABLE FOR WATER-PROOFING, DUST-PROOFING AND HERMETICALLY SEALING OF **CONTAINERS**, CABINS, BUS, MOBILE HOMES AND VARIOUS APPLIANCES.

FEATURES:

- OUTSTANDING DURABILITY.
- ONE PARTS NO MIXING.
- GOOD ADHESION AND EXCELLENT ELASTICITY TO METALS, WOODS, PLASTICS, GLASS AND MANY OTHER ENGINEERING MATERIALS.
- 100% WEATHER PROOF.
- PERMANENTLY FLEXIBLE UNDER STRESS TO NORMAL EXPANSION AND COMPRESSION.
- QUICK CURING AT ROOM TEMPERATURE.
- EXCELLENT GUNNABILITY.
- ♦ VERY STABLE PROPERTIES IN COMPOSITE CONTAINER.

USES:

- FOR JOINTS OF CONTAINERS.
- FOR JOINTS OF AUTOMOBILES, BUS AND OTHER VEHICLES.
- SEALING OF JOINTS IN ZINC ROOFS AND SLATE ROOFS.

WE RECOMMEND PRELIMINARY COMPATIBILTY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS

NOT RECOMMENDED FOR:

N-048 NEOPRENE SEALANT IS NOT SUITABLE FOR HIGH JOINT MOVEMENT SUBSTRATE.

COLOUR:

GREY. OTHER COLOURS ARE AVAILABLE UPON REQUEST.

APPLICATION:

- SURFACE MUST BE CLEAN AND DRY.
- CUT NOZZLE TO DESIRED SIZE.
- INSERT CARTRIDGE INTO CAULKING GUN.
- PUSH SEALANT AHEAD FOR UNIFORM BEAD.
- TOOL WITHIN 5 MINUTES.
- CLEAN OFF EXCESS SEALANT WITH M.E.K. OR TOLUENE.

SPECIFICATION:

BASE APPEARANCE SOLVENT SPECIFIC GRAVITY SOLID CONTENTS SHORE A HARDNESS TENSILE STRENGTH TACK FREE TIME APPLICATION TEMP. SERVICE TEMP. SHELF LIFE NEOPRENE RUBBER NON-SAGGING PASTE AROMATIC SOLVENT BLEND 1.15 ± 0.05 $76 \pm 5\%$ 35 APPROX. 1.2 MPa 10 MINUTES APPROX. -10° C TO 50° C -50° C TO 100° C 12 MONTHS

STORAGE:

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5°C TO +30°C.

CAUTION:

HIGHLY FLAMMABLE. READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.





