

# M-309LSi

For austenite stainless steel (Low carbon, Dissimilar steels)

## Classifications

EN ISO 14343-B:2009	: SS 309LSi	JIS Z 3321:2013	: YS309LSi
AWS A5.9-2012	: ER309LSi		

## Description

- MIG welding of 22%Cr-12%Ni STS and dissimilar steels such as 304L to mild steels or low alloy steels.
- A various application of petrochemical and fiber industrial apparatus.

## Typical chemical composition of wire (%)

C	Si	Mn	Ni	Cr
0.01	0.91	1.86	13.62	23.07

## Typical mechanical properties of all-weld metal

	Y.S (MPa)	T.S (MPa)	El. (%)	IV (J) 0°C	IV (J) -196°C
AWS A5.9		min. 520	min. 30		
EN ISO 14343	min. 320	min. 510	min. 25		
Example	435	609	39	114	56