

Covered Electrodes

K-7018

For 490MPa high tensile steel

Classifications

EN ISO 2560-A:2006	: E 42 3 B 32 H10	KS D 7006	: E5016
EN ISO 2560-B:2006	: E 49 18 A U H10	JIS Z 3211	: E4918
AWS A5.1-04	: E7018		

Description

- Covering is low hydrogen, iron powder type for welding of 490MPa class high tensile steel in ships, bridges, storage tank, building and industrial machinery.
- Excellent mechanical properties and radiographic soundness.
- Satisfactory bead appearance and slag removal.
- Redry the electrode at 300~400°C for 1~2 hours prior to use.

Welding positions



Typical chemical composition of all-weld metal (%)

C	Si	Mn*	P	S	Ni*	Cr*	Mo*	V*	*Sum
0.07	0.61	0.87	0.015	0.011	0.02	0.03	0.01	0.01	0.94

Typical mechanical properties of all-weld metal

	Y.S (MPa)	T.S (MPa)	El. (%)	IV (J)		Remarks
				-20°C	-30°C	
AWS A5.1	min. 400	min. 490	min. 22		≥ 27	
EN ISO 2560-A	min. 420	500~640	min. 20		≥ 47	
Example	480	570	30	100	70	AW

* AW : As-Welded

Sizes available and recommended currents (AC or DC +)

Dia.	(mm)	2.6	3.2	4.0	5.0	6.0
Length	(mm)	350	350	400	400	450
Amp.	F	60~100	90~130	130~180	200~250	250~310
(A)	V · OH	50~80	80~120	110~170	160~210	-

Approvals

ABS	BV	DNV	GL	KR	LR	NK
3YH10,E7018	3YHH	3YH10	3YH10	3YH15	3YmH15	KMW53H

* Others : KS, JIS, CWB, CE