

Extruded E.P.D.M. Rubber

Excellent resistance to ozone, sunlight and aging with good flexibility at low temperature , due to that , it is an ideal material for outdoor service . Excellent resistance to water and steam , but poor resistance to oil , gasoline and hydrocarbon solvents .

Standard Color :	Black		
Work Temperature:	-40 °C - 130 °C		
Specification :	Test Method	Unit	Test Result
Specific Gravity	ASTM D792	g/cm3	1.4+-0.1
Hardness	ASTM D2240	Shore A	71~72
100% Modulus	ASTM D-412	kgf/cm2	73
Tensile Strength	JIS K6301	kgf/cm2	91.7
Elongation	JIS K6301	%	350
Tear Strength	ASTM D-412	kgf/cm	50
Abrasion Resistance, 6 Lb/3300 RPM	ASTM D-1042	C. C.	D. 2.06