



PRODUCT SPECIFICATION	Page :1
	Revised edition no : 02
P-815 GP-800 CONTACT ADHESIVE	Effective Date: 28-11-2015

Description:

P-815 A general purpose contact adhesive, especially for bonding Formica, rubber, cork, leather, fiberglass, polyurethane foam etc.

Physical Properties

Odour	:	Typical toluene smell
Appearance	:	Golden yellow to light brown
Flash Point	:	Typical <-20°C
Solubility	:	Insoluble in water
Shelf life	:	9 months to 1 year from the date of manufacture
Physical hazards	:	Flammable liquid (UN NO 1133 Class 3)

Directions For Use

1. Ensure that surfaces are clean, dry and free from dust, gril, oil or grease.
2. Apply adhesive to both surfaces with a brush or scraper to give a uniform coating.
3. Allow to dry 3 to 20 minutes according to surface porosity.
4. Apply even pressure to the assembly to ensure uniform bonding.
5. Use T-800 thinner or cleaner.

Precaution

- A. Not to be consumed
- B. Keep out of reach of children.
- C. Keep away from fire.
- D. Keep away from direct ultra sunlight and tightly closed the containers after used.

Storage

Keep container sealed when not in used.
Store in cool & dry place and keep away from direct sunlight.
Stable in 9 to 12 month from the of manufacture.

Packing

1 kg & 3 kgs

Note

All recommendations for use of our products, whether given by us in writing, orally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge at the time such recommendations are made. As additional information is learned, these recommendations may be updated. They may also be impacted by circumstances outside our control. Notwithstanding any such recommendations, the user shall remain responsible for satisfying himself that the product as supplied by us are suitable or his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot responsibility therefore. The user shall ensure that the intended use of the products will not infringe any third party's intellectual property rights.

TLC-KOYA CHEMICALS MANUFACTURING SDN BHD

No.22 & 23, Jalan Maju 1, Cemerlang Industrial Estate, 81800 Ulu Tiram, Johor, Malaysia.

Tel: 607-8675798 Fax: 607-8675799

Website: www.koyachemicals.com EMAIL: admin@koyachemicals.com