

IP CONSULTANCY & ENGINEERING SDN BHD (884518-A)

No. 41, Jalan Anggerik Mokara 31/64, Kawasan Industri Kota Kemuning, 40460 Shah Alam, Selangor D.E. Malaysia. Tel: +60351316514 Fax: +60351210964

Email: mnara@jpconsultancy.com.my / enquiry@jpconsultancy.com.my

Web: www.jpconsultancyandengineering.com

TECHNICAL DATA SHEET

JPTM TITANIUM PUTTY

DOCUMENT NO: JP/0212/16

Product type : Two-pack solventless epoxy with titanium fillers

Color : Grey

Mixing ratio : Base - 4: Hardener - 1 (by weight)

Pot life : 15 minutes

Application : Mix compound homogeneously. Only mix desired usage amount from packaging.

Apply via putty knife or fingers with rubber gloves on onto sandblasted or power

brushed surface.

DO NOT ADD THINNER.

Drying Characteristics

Touch dry : 30 minutes Full curing : 24 hours

Finish : Machinable to metallic finish (after 3 hours)

Flash point : Above 300°C

Storage : Up to 24 months in original sealed containers

Packing : 1kg (800g Base, 200g Hardener)

Physical Properties

Specific gravity: 2.0 gm/ccTemperature resistance: 170 °CHardness: 88 DAdhesive Tensile Strength: 2200 psiCompressive strength: 16000 psi

Disposal : Spray into furnace under controlled conditions.

Note: The information given in this bulletin is believed to be reliable. However, the conditions under which our product may be used are beyond our control. Hence, the products are sold with the understanding that purchaser will make their own tests to determine the suitability of the product for their particular use.