

IP CONSULTANCY & ENGINEERING SDN BHD (884518-A)

No. 41, Jalan Anggerik Mokara 31/64, Kawasan Industri Kota Kemuning, 40460 Shah Alam, Selangor D.E. Malaysia. Tel: +60351316514 Fax: +60351210964

Email: mnara@jpconsultancy.com.my / enquiry@jpconsultancy.com.my

Web: www.jpconsultancyandengineering.com

TECHNICAL DATA SHEET

JP WRAP MC/LP (Moisture Cured/Low Pressure)

CERTIFICATE NO: JP/1699/16

No preparation! No downtime! No mess! No risk!

JP Wrap MC/LP is a moisture cured urethane impregnated fiber glass tape repair and maintenance system that sets even under water within 30 minutes of application, depending on temperature.

Product features:

- Applicable in fresh or salt water.
- Non toxic, non combustible and odorless.
- Repairs cracked, broken or leaking pipe carrying petroleum, oil, gasoline and organic solvent (up to 20 Bar at leaking point).
- Applicable in acid or alkaline environment.
- Applicable on metal, plastic, wood, rubber, PVC and glass.
- Can be used as protective shield to reinforce & rehabilitate piping.
- Prevents metal to metal contact which avoids dissimilar metal corrosion, isolating piping from pipe supports.
- Minimizes operational shutdown of industrial equipment / system.

SPECIFICATIONS			
Material	E-Glass (Multiaxial Tape)		
Tensile Strength	25,200 psi		
Compressive Strength	26,900 psi		
Flexural Strength	16,400 psi		
Ply Thickness	0.011 inches (0.28mm)		
Working Time	1 hour package open time, depending on humidity		
Flash Point	142°C (288°F)		
Shelf Life	1 year if stored between 4° - 27°C (40° - 80°F) and if aluminum pack is not punctured		
Sizes	2" x 1.5m and 4" x 4.5m		
TEST PERIOD (2 months)		oC	SURFACE CHANGE
Distilled water		23	None
Sulphuric acid, 50%		23	None
Hydrochloric Acid, 50%		23	Blistering (30 days)
Ammonia, 10%		23	Blistering (30 days)
Gasoline		23	None
Methanol		23	Softening (2 days)
* Other test results could be provided upon request			