

DRI-GARD TZ 300GF

Chemical-, Corrosion- & Abrasion-Resistant Glass Flake Reinforced Epoxy Coating

DRI-GARD TZ 300GF is a two-part, solvent-free, high performance glass flake reinforced epoxy protective coating that protects concrete & metal against chemicals, corrosion & abrasion in aggressive environments.

DRI-GARD TZ 300GF has superior penetrating properties, flexibility and adhesion strength on wet concrete and steel substrates, making it suitable to be used where concrete surfaces are damp and cannot be completely dried out, such as wastewater tanks, tidal zones and splash zones.

Product Data

Appearances / Colors	Grey, Black (Glossy)
Packaging	5kg set
Storage	12 Months from date of production
Storage Condition	Dry conditions at Temperature between +5 - +30 °C. Keep away from direct sunlight.

Technical Data

Origin	Epoxy
Solid Content	98% ± 2%

Application conditions

Theoretical consumption	Approx. 3.0 m ² per kg at 200 microns DFT (Min. 2 coats)
Dry Film Thickness	Recommended thickness: <ul style="list-style-type: none">• 200 microns (normal environments)• 500 microns (severe environments)
Potlife	60 minutes (varies with temperature)

FEATURES/BENEFITS

- ✓ Glass fibre reinforced
- ✓ Excellent resistance against specific chemicals
- ✓ Deep penetration into concrete surface to prevent peeling
- ✓ Excellent adhesion to wet surface
- ✓ Cures underwater
- ✓ Cures at low temperatures
- ✓ Excellent flexibility
- ✓ High build – may be applied up to 250 microns in one coat

APPLICATION AREAS

- ✓ Concrete surfaces
- ✓ Metal surfaces
- ✓ Tank lining
- ✓ Tidal zones
- ✓ Offshore marine & petrochemical services
- ✓ Sheet piles
- ✓ Underground & submarine pipes
- ✓ Waste water tanks
- ✓ Jetty piles
- ✓ Underground tanks



DRITECH CHEMICALS SDN. BHD. (1184082-K)

A-13-02, Atria SOFO Suite, Jalan SS 22/23, Damansara Jaya, 47400, Petaling Jaya, Selangor, Malaysia
TEL: +603 9212 8510, FAX: +603 9212 8519

SUBSTRATE

Remove oil or grease from surface to be coated. Surfaces must be free from any loose and/or friable materials.

Steel: For maximum protection, sand blast to remove surface contaminants and create surface profile of about 50-75 microns.

Concrete: Wet blasting or high pressure water jet blasting is recommended to remove surface contaminants before application of coatings.

APPLICATION & MIXING

Apply by spray, brush or roller. Mix Part A thoroughly, then mix in Part B and mix until homogeneous. Do not break sets. Thinning is not recommended.

TOOLS

Clean all tools and application equipment with thinner immediately after use. Hardened and/or cured material can only be mechanically removed.

HEALTH & SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTE

The information, and the recommendations relating to the application and end-use of these products, are given in good faith based on current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance to the manufacturer recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. The manufacturer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.