

# Galflo CuPAg 15

Copper-phosphorus alloy



EN ISO 17672	EN 1044	DIN 8513	AWS A 5.8
CuP 284	CP 102	L-Ag15P	BCup-5

## Composition, typical analysis (% w/w):

<u>Ag</u>	<u>Cu</u>	<u>P</u>
15	BALANCE	5

## Mechanical and physical properties:

Working temperature:	700	°C
Melting range:	645 –800	°C
Specific gravity:	8.4	g/cm <sup>3</sup>
Tensile strength:	250	N/mm <sup>2</sup> (MPa)
Elongation:	10	%
Electrical conductivity:	7	Sm/mm <sup>2</sup>
Hardness:	/	HV

## Characteristics / Applications:

**Galflo CuPAg15** is a phosphorous-containing brazing alloy with excellent flow characteristics. The brazing alloy is suitable for joining copper to copper or copper-based materials. Due to its phosphorous content, you have not to use an additional flux for brazing only copper to copper. This brazing alloy is not allowed to be used if sulfur containing medias may have contact with the joint during operating. Further it is not allowed to use this alloy for joining steels (Fe) or materials containing iron, nickel cobaltas it will be formed brittle phases in the joint.

In refrigeration and air conditioning industries can be used for service temperatures down to -50°C. It can be used for brazing with flame, with induction heating and in a furnace under protective atmospheres.

Typical applications are found e.g. in the plumbing trade, in the electric industry and for the refrigeration and air conditioning industry.

## Flux:

- SHT

## Delivery Form

Rod	Coated	Wire	Ring	Foil	Powder	Nanotech	Paste
X		X	X	X	X	X	X

Technical Data Sheet – Ver 2.0 - 17/02/2016

**PIETRO GALLIANI BRAZING S.p.A.** Via Molino Malpasso 65, 40038 Vergato (BO) Italy  
Phone +39 051 910061 Fax +39 051 7417223 Email: info@pietrogalliani.com

Cap. Soc. € 4.000.000 i.v. - VAT IT 02788601207 - C.F. 02788601207 R.E.A. BO n. 467613 - Iscr. Reg. Imp. BO n.02788601207