# **Technical Data Sheet**

















# Chaintop MT M

# Fully synthetic high temperature chain oil with added MoS2

#### Description

Chaintop MT M evaporates extremely slow even at temperatures ranging from 200 °C up to 260 °C. Excellent resistance to oxidation provides an exceptional stability at very high temperatures and enables the formation of heavy coking residue to be avoided at temperatures up to 280 °C (short periods up to 300 °C). Provided with anti wear and EP properties, reinforced by a combination of molybdenum disulphide based solids.

### **Applications**

Chaintop MT M is an oil which is specially developed for the lubrication of chains and bearings of systems operating at continuous temperatures between 170 °C and 280 °C (short periods up to 300 °C) and is particularly recommended for:

- Chains of dryers for plasterboard, glasswool, etc.
- Chains and rollers of overhead conveyors
- Textile tenter frames
- Drying machines
- Bakery ovens and on paint stoving chains

#### **Benefits**

- Long wet film life at high temperatures
- Does not form hard carbon deposits
- Good load and anti-wear properties
- Miscible with most ester based fluids

# Typical performance data

	Test method	MT 100 M	MT 220 M
Base oil		Ester	
Kinematic viscosity @ 40 °C, cSt	ASTM D445	100-130	210-230
Colour	-	Dark Grey	Dark Grey
Density, kg/m3	ASTM D1298	960	962
Flash point, °C	ASTM D92	>265	>265
Pour point, °C	ASTM D97	<-25	<-25
Copper corrosion	ASTM D130	1a	1a
Noack weight loss after 1 Hour @ 250 °C, %		1.0	1.0
4-ball, wear test	ASTM D2596		
<ul> <li>Weld load, kg</li> </ul>		225	225
<ul> <li>Load-wear index, kg</li> </ul>		39	39

All performance data on this Technical Data Sheet are indicative only and can vary during production

Matrix Specialty Lubricants BV - info@matrix-lubricants.com – www.matrix-lubricants.com

29/05/2020 Version 1 Page 1 of 1