# **Technical Data Sheet**





## **Grease Calcium Graphite**

#### Calcium based graphite grease

#### Description

Calcium based graphite grease for severe operating conditions. Temperature range - 20 up to 120 °C.

#### Applications

• Grease Calcium Graphite 3 is intended for lubrication of the

Typical performance data

### pantograph sheet iron as conductive calcium grease

#### Approvals

Grease Calcium Graphite 2 & 3 are approved by RENFE and by METRO MADRID (Madrid subway)

	2	3
Thickener, soap type	Calcium	Calcium
Base oil type	Mineral	Mineral
Base oil viscosity @ 40 °C, cSt	35	35
NLGI consistency class,	2	3
Penetration 60w, @ 25 °C	265/295	220/250
Working stability, after 10 <sup>6</sup> w	+/-15	+/-15
Dropping point, °C minimum, °C	120	120
Sulphated ashes, %	2.5	2.5
Water content, max, %	0.5	0.5
Free alkalinity, in Ca(OH) <sub>2</sub> , max, %	0.3	0.3
Water washout resistance, %	5	5

All performance data on this Technical Data Sheet are indicative only and can vary during production **Matrix Specialty Lubricants BV - info@matrix-lubricants.com – www. matrix-lubricants.com**