## **Technical Data Sheet**

















### **Paste ASLA**

#### High performance anti seize and conductive paste

#### Description

Paste ASLA is intended specifically for the lubrication of threaded joints under very severe operating conditions. Thanks to its superior electric conductivity it is also perfectly suitable for the lubrication of connectors in high voltage applications. The lubricating film that Paste ASLA builds will avoid metallic adherence, micro welding, pitting and seizing. Thanks to its superior anticorrosive capacity it will also avoid oxidative build-up on the sliding surface of moving parts as a result of electric conductivity.

Paste ASLA shows excellent suitability at humid environments, especially with salt water. It is particularly suitable for windmills – especially those at sea - and offshore applications where it offers extended protection from corrosion.

#### **Applications**

- Threaded joints subject to high pressures and temperatures
- Threaded joints subjected to high torques
- Drilling head screws
- High voltage electrical connectors
- Connectors and electrical devices requiring a conductive lubricant with high anticorrosive capacity
- Mounting paste

#### **Benefits**

- High thermal stability
- Superior behaviour to high pressures and high temperatures
- · High electrical conductivity
- Excellent resistance to (sea) water
- High sealing capacity
- Wide range of operating temperatures (-25 to 140 °C), dry lubrication up to 1100 °C

All performance data on this Technical Data Sheet are indicative only and can vary during production

Matrix Specialty Lubricants BV - info@matrix-lubricants.com – www.matrix-lubricants.com

19/10/2018 Version 1

# **Technical Data Sheet**

















#### Typical performance data

	ASLA
Colour	Metal grey
Thickener	Lithium
Base oil type	Mineral
Base oil viscosity @ 40 °C, cSt	300
Penetration @ 25 °C, x 0,1 mm	290-320
NLGI consistency	1-2
Dropping point, °C	>180
Solids type	Several
Solids content, %	>30
Dynamic viscosity, mPa.s	4000-6000
Oil separation, 7 days/40 °C, %	5
Water washout, 40 °C, %	2
<ul> <li>4-ball wear test</li> <li>Welding load, kg</li> <li>Wear scar dm, 1'180°C, mm</li> </ul>	>700 0.5
Corrosion on metals, 8'/140 °C  • Steel  • Aluminium  • Copper-aluminium	Nil Nil Nil
SRV test: 250 N/1mm/20 Hz/50 °C/1hour /ring-plate:     Friction coefficient minimum     Friction coefficient maximum     Friction coefficient final	Max 0.075 Max 0.180 Max 0.075
Service temperatures, °C	-25 – 140
Peak temperature (dry), °C	1100