


SUN-FOIL®

Woven Series

New and Improved Version

Certified by CIDB



Excellent Reflectivity



Chicken Wire Mesh
(Not Required)



Light Weight
(Yet Heavy Duty)



Edge Tear Resistance
(Resulting in Low Wastage)



Moist Barrier
Non-Delamination
(When Soak In Water)



Easy Installation
(Cost Effective)

SN3-CLASS 'O'

Product Description

SUN-FOIL® SN3-Class 'O' is used as insulation against radiant heat transfer and can be used to its greatest advantage in instances where radiation is the predominant means of heat transfer.

SUN-FOIL® SN3-Class 'O' is an excellent reflector of all long wave radiant heat that strikes it - **REFLECTIVE OF UP TO 98%** of all radiant heat.

Fire Attributes

SN3-Class 'O' is classified as Class "O" in accordance to fire tests on building material and structures.

- British Standard, BS 476-6 : Fire Propagation Test
- British Standard, BS 476-7 : Surface Spread of Flame Test

Thermal Properties

SN3-Class 'O' is tested in accordance to MS 2095, ISO 8301 / MS ISO 8302 for thermal resistance, R-value 1.243 m²K/w

Awards & Certificates

- Malaysia Standard - MS 2095, SIRIM QAS International Sdn. Bhd.
- ISO 9001: 2015, Guardian Independent Certification
- Jabatan Bomba dan Penyelamat Malaysia
- CIDB Malaysia
- Malaysia Green Building Confederation (MGBC)
- Asian Reflective Foil Association (ARFA)



SIRIM
MS 2095



BOMBA



ISO 9001 : 2015



BUATAN
MALAYSIA

CIDB PPS REG. NO:
1160504ML0121

WOVEN FOIL (Fire Retardant)

SUN-FOIL® SN3-Class 'O' is double sided made by high reflectivity pure aluminium bonded with a layer of FR HDPE woven fabric and high quality reflective aluminium film by special FR bonding material. It provides excellent insulation properties and effective radiant barrier.

SUN-FOIL® SN3-Class 'O' is designed light-weight. It is easy to install as it does not require mesh due to high tensile strength and edge tear resistance.

SUN-FOIL® SN3-Class 'O' is also flame retardant, waterproof, non-toxic, bacteria free, fungus and corrosion resistant.

TECHNICAL DATA			
Description	Test Method	Unit	Value
Grammage	In House	g/m ²	160 ± 30
Thickness	In House	µm	150 ± 30
Tensile Strength	AS/NZS 1301:448s	kN/m	MD ≥ 10.0 ± 1.0 CD ≥ 10.0 ± 1.0
Edge Tear	TAPPI T470	N	MD ≥ 300 ± 50 CD ≥ 300 ± 50

Technical Information provided represent average result of tests conducted under standard procedure and is subject to variation. No guarantee can be made regarding specific applications or patent rights.

FIRE RETARDANT TEST FOR SN3-Class 'O'

CHARACTERISTIC	TEST METHOD	SPECIFICATION
Fire Propagation of Material Sub-Index, i_1, i_2, i_3 Overall Performance Index	BS 476 ; Part 6	< 6 < 12 (Sirim Report 2019FE0452)
Surface Flame Spread Test	BS 476 ; Part 7	Class 1 (Sirim Report 2019FE0451)
Classification of Fire Hazard		Class O



SN3-CLASS 'O'

Standard Roll Size: W 1.25m x L 48m



- Pure Aluminium
- FR PE Tie Layer
- FR HDPE Woven Fabric
- FR PE Tie Layer
- Aluminium Film



DEXSTEEL (M) SDN BHD (1492281-M)

No. 5, Jalan PP 2/1, Taman Putra Prima, 47100 Puchong, Selangor Darul Ehsan, Malaysia.

Tel: +6 016-7894756 Email: dexsteelroof@gmail.com