

GOODY EASY CLEAN

DURABILITY WASHABLE PAINT

Product Name	GOODY EASY CLEAN
Product Description	GOODY Easy Clean is a high grade emulsion that gives a bright, smooth and attractive mid sheen pearl finish for interior use. GOODY Easy Clean can withstand moderate washing which makes it ideal for surfaces where regular cleaning is required.
Designed Use	For use on new or previously painted interior masonry surfaces such as brickwork, plaster and cement rendering where regular cleaning is a pre-requisite.
Binder Type	Acrylic emulsion
Performance	<ul style="list-style-type: none"> • Easy wipe up to 5,000 times • Bright, smooth, pearl finish • Withstand moderate washing • Dirty hand marks can be wiped clean • No added lead or mercury • Low VOC and odour
Physical Properties Coverage* Volume Solids Dry Film Thickness Wet Film Thickness	10 – 12 m ² /Lt @ 25 microns 35% 25 microns / coat 63 microns / coat
Finishing Colours Finishing Pack Size	Refer to Kansai Paint's colour card Attractive mid sheen pearl finish 1, 5 & 15 litres
Application Drying Times Dilution Cleaning Up	Surface dry : 20 mins ; Recoat : 1 - 2 hours <i>*Depend on temperature and humidity</i> Clean household water Clean household water
Dilution Ratio Brush or Roller Conventional Spray Airless Spray	Ready for use. If dilution is required, add up to 5% clean water. Dilution up to 10% water. Ready for use.
Spray Equipment Guide Conventional Spray Airless Spray	A typical set up would be a minimum atomising pressure of 2.8 kg/cm ² and fluid pressure of 0.4 kg/cm ³ with a nozzle size of 0.43 mm. A typical set up would be a minimum of 155 kg/cm ³ with nozzle size of 0.38 - 0.43 mm and a spray tip angle of 65°.
Surface Preparation	<p>New, unpainted surfaces Allow surfaces to cure and dry out at least 28 days. Large cracks must be repaired with cement: sand mix and rendered smooth. Make good all minor defects with appropriate fillers. Remove all loosely adhering residues by thorough brushing.</p> <p>Repainting Check for powders or chalk. These surfaces contaminants must be completely removed by washing with warm water and detergent solutions. Rinse with clean water, taking care to change the rinsing water</p>

regularly. If after thorough washing the surface is still slightly powdery, it may be necessary to seal it with PAR Plasterseal solvent based wall sealer. Dilute the sealer up to 30% and apply liberally to allow the sealer to fully penetrate the surface and form a barrier that seals up the chalk.

Recommended Paint System

New, unpainted surfaces :

1 st		2 nd & 3 rd	
GOODY AR Wall Sealer	Recoat 1 - 2 hours	GOODY Easy Clean	Recoat 1 - 2 hours

Repainting :

1 st		2 nd & 3 rd	
PAR Plasterseal	Recoat 4 - 5 hours	GOODY Easy Clean	Recoat 1 - 2 hours

NB : GOODY AR Wall Sealer and PAR Plasterseal work best on surfaces with a moisture content of below 15% and alkalinity below pH-9, otherwise premature paint failure may occur.

Limitations : Not suitable for use in areas subject to frequent or heavy condensation, e.g : in some kitchens and bathrooms.

Safety & Health Information

- Ensure adequate lighting and ventilation during application and drying.
- This product does not contain added lead or mercury.
- When applying paints, it is advisable to wear eye protection.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- Use soap and water to remove splashes from skin.
- Storage: Keep container closed and store in clean and dry conditions.
- Dispose of contents and container in accordance with all local, regional, national and international regulations.
- Do not empty into drains or water courses.
- This product is not flammable. Keep out of reach of children.
- Safety Data Sheet (SDS) is available upon request.

For further information on Product Data, please contact :

Decorative Sales Department

Kansai Paint Asia Pacific Sdn. Bhd. (705919-W)

4, Solok Waja 2, Kawasan Perindustrian Bukit Raja, 41710, Klang, Selangor, Malaysia.

Website : www.kansaimalaysia.com Tel : +60 3 3362 2388 Fax : +60 3 3342 7223

**Practical coverage will vary according to the roughness and porosity of surface to be painted, the application method and condition, dry film and thickness and the skill of applicator.*

The information in this technical data sheet is given to the best of our knowledge based on laboratory testing and practical experience and is provided as a general advice only. No guarantee of results is implied since the conditions of use are beyond our control. It is the responsibility of the users to ensure the suitability and proper usage of the product. We reserve the right to change the data without prior notice.